

SAERflow combines a glass reinforcement and a lightweight synthetic structure. Together, they provide uncompressible layers with excellent resin flow and high draping properties. SAERflow is used as an internal flow media, which saves a tremendous amount of time. No need to lay-up or release the external flow mesh or its associated consumable layers.

- 1 Benefits of an external flow mesh integrated
  The flowing capacity of SAERflow is impressive. //
  SAERflow resin flow is up to twice as fast as
  - SAERflow resin flow is up to twice as fast as comparable material. // It is ideal for vacuum infusion. // SAERflow is equivalent to and replaces an external flow mesh.
- Saves time and money

No need for an external flow media. // No peel-ply necessary. // Saves up to 50% of handling costs.

Very good drapability


Because of its highly deformable properties, SAER-flow can be easily draped while its original flow and mechanical properties are kept intact.


Comparable bending properties

The bending properties of a laminate with SAERflow are comparable to those of a pure NCF laminate.

Can be combined with other SAERTEX solutions
SAERflow can be combined with other SAERTEX
solutions, e.g. glass, carbon and aramid NCF's. // It is
produced to fit your application.







TECHNICAL DATA	SAERflow BX304
Bending modulus (in %)*	89.0
Bending strength (in %)*	93.8
STANDARD	
Process	Infusion
Resin intake	0.8 kg/m²
Thickness	0.9 mm
Weight	304 g/m²
COMPONENTS	
Flow medium	BX304
Drape support**	CSM150
Material	Glass (>75%) + synthetic
WIDTHS	
Standards	1,270 mm – 2,540 mm
Individual Tapes	On request

